



www.qmarkings.co.uk

Resin Bound Aggregate

Private Driveways

Typical base build up for turning driveways

0.5mm dia grit cast onto uncured surface

Surface Course

Hand applied and trowelled to a smooth finish by QMS Trained Operatives



The typical depth of resin bound paving surface

3mm aggregate formulation requires a minimum of **16mm**

6mm aggregate formulation requires a minimum of **18mm**

10mm aggregate formulation requires a minimum of **24mm**

Binder Course

Laid by others in well compacted layer to a minimum fall of 1.5%.



A 50mm depth of AC 14 close surf asphalt concrete max 100/150 pen to BS EN 13108-1:2006. (Bituminous Macadam).

Sub-base

laid by others in well compacted layers to a minimum fall of 1.5%.



A 150-225mm Depth of well compacted non-frost susceptible Type 1 granular sub base to SHW clause 803 or locally available secondary or recycled aggregates which comply with the requirements of the specification for Highway works for sub-bases.

Membrane*

A Terram 1000/900/Advantage geotextile membrane to prevent upward migration of fine soil particles *(optional).



Sub-grade



Quality Marking Services Limited
3 Fairfax Road, Heathfield Industrial Estate
Newton Abbot, Devon TQ12 6UD

T 01626 836777
F 01626 836774
info@qmarkings.co.uk



Any Surface... We've got it covered!

NOTE: A suitable steel, wood, brick, stone or aluminium edging should be provided to ensure a neat edge detail.

Any advice, recommendation or information given by Quality Marking Services Limited is based on practical experience and is believed to be accurate at the time of publication, no liability or responsibility of any kind (including liability for negligence) is accepted in this respect by the company, it's servants or agents.

The figures quoted do not constitute a specification, they represent typical values obtained for this product.